



Cande Shop, LLC  
770 Big Tree Dr  
Unit 112  
Longwood, FL 32750  
Phone (407)692-8116

www.candeshop407.com

## Triple C Intercoat

## TECHNICAL DATA

### Intercoat Clear

#### DESCRIPTION:

**Triple C Intercoat** clear is a universal product that can be used as a wet-bed sealer, lock-down clear, cut-in clear, mid-coat for tri-coats, graphics and basecoat blender. Compatible with most basecoat systems and can be reduced with standard and reactive reducers.



#### FEATURES:

- ✓ Lock-down clear; reduces mottling
- ✓ used with basecoat, tri-coats, pearls and metallics
- ✓ Fast dry cut-in clear in areas not exposed to sunlight
- ✓ Wet bed sealer; better adhesion, better color match

#### INSTRUCTIONS:

**Note: Triple C Intercoat should be reduced with the same type of reducer that was used in the basecoat. If reactive reducer was used in the basecoat, reduce Triple C with reactive reducer. If urethane grade reducer was used in the base, use urethane grade reducer in the Triple C. Also, if a basecoat activator was added to the basecoat, add basecoat activator to the Triple C.**



#### Lock-down clear

Reduce **Triple C** 1:1 with appropriate reducer. Apply 1 light coat to lock down the metallic/pearls. Allow 10 minutes to dry before applying the clearcoat

#### Color Blender

Reduce **Triple C** 1:1 with appropriate reducer. Add 1 part **Triple C** reduced mixture to 1 part reduced basecoat.

Apply 1-2 coats of this mixture on the blend area extending each coat a little further out on the blend area. Allow 10 minute flash time between coats.

Allow 15 minutes dry time before applying clearcoat.

#### Cut-In Clear

Reduce **Triple C** 1:1 with appropriate reducer. Apply basecoat color and allow to dry according to paint manufacturer's recommendations. Apply 2-3 coats of reduced **Triple C**. Allow 10 minutes flash time between coats.

**Note: Do not apply in areas that will be exposed to direct sunlight.**

#### Mid-coat / Intercoat clear

Apply basecoat or color coat and allow to dry according to paint manufacturer's recommendations. Reduce **Triple C** 1:1 with appropriate reducer and apply 1-2 light coats. Allow to dry 15 minutes and apply next coat of color.





Cande Shop, LLC  
770 Big Tree Dr  
Unit 112  
Longwood, FL 32750  
Phone (407)692-8116  
www.candeshop407.com

**Triple C Intercoat is not compliant in California**

## TECHNICAL DATA

Color	Water Clear
Activator/Hardener	N/A
Reducer	R-60, R-70,R-80 or R-90
Mix Ratio	1:1
Pot Life	N/A
Number of Coats	N/A
Flash Time	N/A
Recoat w/o sanding	N/A
Dry to Sand	N/A
Air Dry 70°F (21°C) 50% RH	N/A
Force Dry	N/A
Gun Set-Up Gravity Feed (HVLP)	1.3-1.4mm
Air Pressure @ Gun (HVLP)	8 – 10 psi
Air Pressure @ Gun (Conventional)	40 -45 psi
V.O.C. Limit <b>Canada &amp; California</b>	4.5 lbs/gal (540 g/l)
Sprayable V.O.C.*	
Actual	5.98 lbs/gal (717 g/l)
Regulatory	5.98 lbs/gal (717 g/l)
% Solids Sprayable by Weight	%
Cov. Sq. Ft. / gal @ 1 mil*	N/A
Shelf Life	12 months



Material Safety Data Sheet (MSDS) is available on our website [www.candeshop407.com](http://www.candeshop407.com)

**Triple C Intercoat  
05/2021**